



---

MANUFACTURING OF WATERPROOFING PRODUCTS - CEMENT ADDITIVES  
FLASHBAND - WATER SHIELD - POWER LIFT - OXIDES

---

## Basic Data for Blue Pigment

### Specifications

<b>Moisture</b>	<b>2 %</b>
<b>Fineness</b>	<b>2.1% on 53 microns(300 mesh)</b>

### Analysis

<b>Oil Absorption</b>	<b>17-20 %</b>
<b>pH</b>	<b>7-7.5</b>
<b>Specific Gravity</b>	<b>4.2</b>
<b>Barium (BaO)</b>	<b>54.6 %</b>
<b>Sulphur (SO<sub>3</sub>)</b>	<b>26.5 %</b>
<b>Silicon (SiO<sub>2</sub>)</b>	<b>8.6 %</b>
<b>Total Iron (Fe<sub>2</sub>O<sub>3</sub>)</b>	<b>1.31 %</b>
<b>Magnesium (MgO)</b>	<b>3.0 %</b>
<b>Other Elements</b>	<b>5.99 %</b>