



MANUFACTURING OF WATERPROOFING PRODUCTS - CEMENT ADDITIVES
FLASHBAND - WATER SHIELD - POWER LIFT - OXIDES

Basic Data for Green Pigment 225

Specifications

Moisture	2 %
Fineness	2.0 % on 53 microns (300 mesh)

Analysis

Oil Absorption	15-20 %
pH	7-7.5
Specific Gravity	4.2
Barium (BaO)	53.3 %
Sulphur (SO₃)	26.1 %
Silicon (SiO₂)	9.0 %
Total Iron (Fe₂O₃)	1.79 %
Magnesium (MgO)	3.2 %
Other Elements	6.61 %