



MANUFACTURING OF WATERPROOFING PRODUCTS - CEMENT ADDITIVES
FLASHBAND - WATER SHIELD - POWER LIFT - OXIDES

Basic Data for Yellow Pigment Y47(Kalahari)

Specifications

Moisture	2-3 %
Fineness	0.42 % on 53 microns (300 mesh)

Analysis

Oil Absorption	28.34 %
pH	7.1
Specific Gravity	5.3
Total Iron (Fe₂O₃)	58.36 %
Silicon (SiO₂)	22.5 %
Aluminium (Al₂O₃)	6.96 %
Potassium (K₂O)	0.59 %
Phosphorus (P₂O₅)	0.45 %
Calcium (CaO)	0.36 %
Titanium (TiO₂)	0.25%
Magnesium (MgO)	0.1 %