



MANUFACTURING OF WATERPROOFING PRODUCTS - CEMENT ADDITIVES
FLASHBAND - WATER SHIELD - POWER LIFT - OXIDES

Basic Data for Red Pigment A7

Specifications

| | |
|-----------------|---------------------------------------|
| Moisture | 1 % |
| Fineness | 0.2 % on 53 microns (300 mesh) |

Analysis

| | |
|---|----------------|
| Oil Absorption | 16.8 % |
| pH | 6.4 |
| Specific Gravity | 3.42 |
| Total Iron (Fe₂O₃) | 49.85 % |
| Silicon (SiO₂) | 32.16 % |
| Aluminium (Al₂O₃) | 10.55 % |
| Titanium (TiO₂) | 0.61 % |
| Potassium (K₂O) | 0.55 % |
| Magnesium (MgO) | 0.45 % |
| Calcium (CaO) | 0.14 % |
| Phosphorus (P₂O₅) | N/A |