



MANUFACTURING OF WATERPROOFING PRODUCTS - CEMENT ADDITIVES
FLASHBAND - WATER SHIELD - POWER LIFT - OXIDES

Basic Data for Spanish Red

Specifications

Moisture	2 %
Fineness	2 microns

Analysis

Oil Absorption	10.6 %
pH	8.5
Ferric Oxide(Fe₂O₃)	80-82 %
Silicon(SiO₂)	8.75 %
Calcium(CaO)	3.06 %
Aluminium(Al₂O₃)	2.55 %
Magnesium(MgO)	1.62%
Potassium(K₂O)	0.23 %
Sodium	0.02 %
Chlorides	0.002 %