



MANUFACTURING OF WATERPROOFING PRODUCTS - CEMENT ADDITIVES
FLASHBAND - WATER SHIELD - POWER LIFT - OXIDES

Basic Data for Red Pigment R950 (TERRACOTTA)

Specifications

Moisture	< 2 %
Fineness	0.1 % on 53 microns (300 mesh)

Analysis

Oil Absorption	30.3 %
pH	6.7
Specific Gravity	3.92
Total Iron (Fe₂O₃)	63.0 %
Silicon (SiO₂)	22.6 %
Aluminium (Al₂O₃)	6.3 %
Potassium (K₂O)	0.8 %
Phosphorus (P₂O₅)	0.53 %
Titanium (TiO₂)	0.52 %
Calcium (CaO)	0.36 %
Magnesium (MgO)	0.2 %