



MANUFACTURING OF WATERPROOFING PRODUCTS - CEMENT ADDITIVES
FLASHBAND - WATER SHIELD - POWER LIFT - OXIDES

Basic Data for Yellow Pigment

Specifications

Moisture	2-3 %
Fineness	0.42 % on 53 microns (300 mesh)

Analysis

Oil Absorption	34.2 %
pH	7.3
Specific Gravity	3.4
Silicon (SiO₂)	42.4 %
Total Iron (Fe₂O₃)	32.5 %
Aluminium (Al₂O₃)	11.6 %
Potassium (K₂O)	1.17 %
Calcium (CaO)	1.09 %
Titanium (TiO₂)	0.62 %
Phosphorus (P₂O₅)	0.19%
Magnesium (MgO)	0.1 %